

LANXESS Deutschland GmbH / 51369 Leverkusen

Lentex S.A.

ul. Powstańców Śląskich 54
42-700 Lubliniec

Polska

Biostabilność wykładziny winylowej typ „DELTA”

Szanowny kliencie,

Niniejszym stwierdzamy, że próbki typu

„DELTA” poddane działaniu 0.3% Biochek® 8064
w stosunku do ciężaru całego materiału

przeszły badanie ISO 846 B, jak również ISO 846 C, które zostały przeprowadzone
w laboratoriach LANXESS Material Protection BIO-TM-IP 2 z następującymi
wynikami:

Badana próbka	Ocena ISO 846 B	Ocena intensywności rozwoju
DELTA	0 / 0	Brak widocznego rozwoju grzyba pod mikroskopem

Badana próbka	Ocena ISO 846 C	Ocena intensywności rozwoju
DELTA	0 / 0	Brak widocznego rozwoju bakterii pod mikroskopem

Na podstawie wyników wykonanych badań ISO 846 niniejszym potwierdzamy, że
wykładzina podłogowa „DELTA” wykazuje dobra stabilność biologiczną.

Z poważaniem
LANXESS Deutschland GmbH


Dr. Hermann Uhr
Manager Technical Marketing
Formulation & High Tech


Sandra Schult
Technical Manager IP 2
Industrial Preservation
Business Line Biocides

August 25, 2014

LANXESS Deutschland GmbH
Sandra Schult
BIO-TM-IP2 / Material Protection
Products
Q18 / 566
Chempark
51369 Leverkusen, Deutschland

Phone +49 (0)214 30 33531
Fax +49 (0)214 30 34341
sandra.schult@lanxess.com
www.lanxess.com

Executive Board:
Matthias Zachert
(Chairman)
Dr. Bernhard Düttmann
Dr. Rainier van Roessel

Chairman of the Supervisory
Board:
Dr. Rolf Stomberg

Registered Office: Cologne
Local Court Cologne
HRB 52600
VAT ID no. DE 814 000 384

LANXESS Deutschland GmbH / 51369 Leverkusen

Lentex S.A.

ul. Powstancow Slaskich 54
42-700 Lubliniec

Poland

Biostability of vinyl flooring type "DELTA"

Dear valued customer,

We herewith state that the samples of the type

"DELTA" treated with 0.3% Biochek® 8064
with respect to the weight of the whole material

passed the ISO 846 B as well as the ISO 846 C test which were conducted in the laboratories of LANXESS Material Protection BIO-TM-IP 2 with the following results:


Tested sample	Evaluation ISO 846 B	Evaluation Intensity of Growth
DELTA	0 / 0	No fungal growth apparent under the microscope

Tested sample	Evaluation ISO 846 C	Evaluation Intensity of Growth
DELTA	0 / 0	No bacteria growth apparent under the microscope

Based on the results of the performed ISO 846 testings we hereby confirm that the "DELTA" floor covering showed a good biostability.

Yours sincerely,
LANXESS Deutschland GmbH


Dr. Hermann Uhr
Manager Technical Marketing
Formulation & High Tech


Sandra Schult
Technical Manager IP 2
Industrial Preservation
Business Line Biocides

August 25, 2014

LANXESS Deutschland GmbH
Sandra Schult
BIO-TM-IP2 / Material Protection
Products
Q18 / 566
Chempark
51369 Leverkusen, Deutschland

Phone +49 (0)214 30 33531
Fax +49 (0)214 30 34341
sandra.schult@lanxess.com
www.lanxess.com

Executive Board:
Matthias Zachert
(Chairman)
Dr. Bernhard Düttmann
Dr. Rainier van Roessel

Chairman of the Supervisory
Board:
Dr. Rolf Stomberg

Registered Office: Cologne
Local Court Cologne
HRB 52600
VAT ID no. DE 814 000 384